



ChemTools 8454 Cyanoacrylate Adhesive

ChemTools 8454 is an ethyl cyanoacrylate adhesive of gel consistency for non-drip and non-run applications. It is specially formulated for difficult to bond surfaces.

Applications:

- Suitable for bonding porous or absorbent materials such as wood, paper, leather and fabric.
- Excellent adhesion to metal, plastic and elastomeric compounds.

Bonds:

| | | |
|---------------|-----------------|-------------------|
| ■ Acrylic | ■ Polycarbonate | ■ Paper |
| ■ PVC | ■ Leather | ■ Fabric |
| ■ Polysulfone | ■ Wood | ■ Latex |
| ■ Steel | ■ Aluminum | ■ Zinc Dichromate |

Bonding Times:

Under normal conditions, the surface moisture initiates the curing process. Functional strength developed in a short time but curing continues for at least 24 hours before full chemical/solvent resistance is developed. The rate of cure will depend on substrate used.

| | | | |
|-----------------|---------------|----------------|--------------|
| Stainless Steel | 5-20 seconds | Aluminum | 2-10 seconds |
| Polycarbonate | 10-40 seconds | PVC | 2-10 seconds |
| Neoprene | > 5 seconds | Wood | 2-10 seconds |
| ABS | 2-10 seconds | Nitrile Rubber | >5 seconds |

Physical Properties:

Liquid

| | |
|--|--|
| Composition | Surface Insensitive Ethyl Cyanoacrylate Adhesive |
| Appearance | Colorless liquid |
| Viscosity@ 25°C, cps (Brookfield LVF, Spindle 1-60 rpm) | Gel |



Cured Adhesive

| | |
|---------------------------|-------------------------|
| Gap Filling | 0.75 mm |
| Tensile Shear Strength | 15-26 N/mm ² |
| Service Temperature Range | -40 to + 85°C |
| Full Cure | 24 hours |
| Melting Point Temperature | 160 to 170°C |

Mechanical Properties

| | |
|--|-----------------------|
| Glass Transition Temperature, ASTM E228 | 120°C |
| Dielectric Strength, ASTM D149, v/mil | 625 |
| Coefficient of thermal expansion, ASTM D696, K ⁻¹ | 80 x 10 ⁻⁶ |
| Coefficient of thermal conductivity, ASTM C177, Wm ⁻¹ K ⁻¹ | 0.1 |

Shear Strength, ASTM D1002/DIN 53283

| | |
|--------------------|---------------------------|
| Woods | 25 – 27 N/mm ² |
| Grit Blasted Steel | 18 – 28 N/mm ² |
| Neoprene Rubber | 10 – 18 N/mm ² |
| PVC | 3 – 9 N/mm ² |
| Etched Aluminum | 11 – 19 N/mm ² |
| Polycarbonate | 5 – 20 N/mm ² |

Application Method:

- All surfaces must be clean, dry, dust and grease free. Best result will be achieved with surfaces that have been lightly abraded immediately prior to bonding.
- If using accelerator apply to one component surface only. Apply thin film of adhesive to the other surface and bring the pieces together immediately. Hold for few seconds without disturbing the joints.
- Thin bond lines favor high cure speed. Increasing the bond gap will slow down the rate of cure.

Storage:

Anaerobic adhesives shall be ideally stored in a cool, dry place in unopened containers at a room temperature between 7°C to 28°C. Please do not return any unused material to its original container.

PRECAUTIONS: This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheets (MSDS) for this and all other products being used are understood by all persons who will work with the material.

Warranty: All products purchased from or supplied by ChemTools are subject to terms and conditions set out in the contract. ChemTools warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by ChemTools is considered accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. ChemTools makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent.

ChemTools Pty Ltd – PO Box 4319 – Penrith NSW 2750
ABN 12 114 400 083
Ph 02 4735 3126 – Fax 02 4735 3746
info@chemtools.com.au – www.chemtools.com.au